



BC-THAI-660
Issue: 2
Date: 22nd February 2021
Replaces: 24th Jan., 2019

BIRLA CARBON THAILAND
General Shipping Specification

Grade: **N-660**

<u>Analyticals:</u>	Minimum	Maximum	Target	ASTM Test Procedures
Iodine Adsorption Number, mg/g	<u>31.0</u>	<u>41.0</u>	<u>36.0</u>	D1510
Oil Absorption Number, cc/100g	<u>85.0</u>	<u>95.0</u>	<u>90.0</u>	D2414
Heat Loss, % (As Packaged)	<u></u>	<u>1.0</u>	<u></u>	D1509
Sieve Residue, #35, ppm	<u></u>	<u>10</u>	<u></u>	D1514
#325, ppm	<u></u>	<u>1000</u>	<u></u>	D1514
Pellet hardness (avg), gf	<u>12</u>	<u>51</u>	<u></u>	D5230
Ash Content in Carbon Black, %	<u></u>	<u>0.75</u>	<u></u>	D1506

Issued By:

Sophon B.
Quality Assurance Head

Uncontrolled if printed

Birla Carbon (Thailand) Public Co., Ltd.

Factory : 44 Moo-1, Ayuthaya-Angthong Highway, T. Posa, A. Muang, ANGTONG-14000 Tel : (66) 3567 2150 – 4, Fax : (66) 3567 2148

โรงงาน : 44 หมู่ 1 ถนนอยุธยา-อ่างทอง ตำบล โพสะ อำเภอ เมือง จังหวัด อ่างทอง-14000 โทร. 0-3567 2150 – 4, แฟกซ์ : 0-3567 2148

Bangkok Office : Mahatun Plaza, 12th Floor, 888/122, 888/128 Ploenchit Road, Patumwan, BANGKOK-10330 Tel : (66) 2253 6745 – 54, Fax : 2254 9031, 253 2812

สำนักงาน : ชั้น 12 อาคารมหาทุนพลาซ่า 888/122, 888/128 ถนนเพลินจิต ลุมพินี ปทุมวัน กรุงเทพฯ 10330 โทร : 0-2253 6745 - 54 แฟกซ์ : 0-2254 9031, 0-2253 2812